

TECHNICAL DATA SHEET

- Jointing Systems
- Polythene Builders Film
- Formwork
- Formworking Accessories
- Nails
- Tie Wire
- Loop Ties
- Waterproofing

P: 1300 ALLCON (255 266)
E: sales@allcongroup.com.au

www.allcongroup.com.au

RT Primer

DESCRIPTION

Set-Up RT Primer is a proprietary blend of viscous bitumen resins and tacifiers dispersed in a refined hydrocarbon barrier. RT Primer is used as the prepriming agent for Set-Up Bitumen Road Tape.

APPLICATION

If asphalt or concrete surface has a heavy aggregate surface texture, we recommend the use of SET-UP RT PRIMER as a prime coat direct to substrate to fill surface irregularities providing strong intimate contact with bitumen tape compound.

FEATURES

- Fast Drying
- Highly resistant to mineral acids, salts and alkalis
- Promotes adhesion for bitumen & butyl tape systems
- Brush / Roller / Sponge / Squeegee or spray applied
- Fills surface irregularities providing strong intercoat contact with bitumen or butyl tape compounds.

ESTIMATING & SIZES

Set-up RT Primer is available in 20L drums and should be applied at a rate of 8-10 m² / litre.

INSTALLATION STEPS

1. Thoroughly stir RT PRIMER before use to ensure uniformity of mix.
2. Ensure all surfaces are well cured and dry and all loose material is removed from the surface.
3. Brush, spray or sponge apply an even coating of RT PRIMER at a rate of 8-10m² per litre.
4. Allow to dry for 30mins before applying bitumen or butyl tape.

PROPERTIES

Property	Result
Specific Gravity	0.94
Volume Solids	62% (Approx)
Drying Time (Tack Dry)	10-15 mins @ 25°C
Coverage	8-10m ² / litre
Application Temp	-5°C to 55°C

DISCLAIMER

Set-Up products are manufactured to the highest quality, and if used in the correct applications and in accordance with all directions, will produce quality and consistent results. However Allcon Group Pty Ltd accepts no responsibility for inappropriate usage or faulty workmanship by the end user.

Product: Bitumen Road Tape
Issue Date: 22 September 2023