

TECHNICAL DATA SHEET

- Coatings
- Curing
- Waterproofing
- Moisture Proofing
- Protection
- Repair Products
- Primers
- Repellent

BossCure 800

DESCRIPTION

BossCure 800 is a wax based curing compound forms an impervious film over the surface of freshly finished concrete. BossCure 800 satisfies the requirements of AS3799 standard for curing achieving water retention of greater than 90% and will remain on the surface for 30-35 days before breaking down in sunlight (UV Light).



AREAS OF APPLICATION

- For curing all freshly laid concrete either smooth or textured, indoors or outdoors
- Can also be used as a debonding agent when applied to the concrete sub base prior to pouring the concrete base. This allows the two layers to expand and contract independently preventing cracking.

FEATURES & BENEFITS

- Complies to AS3799 Standard for concrete curing.
- Achieves water retention of 90% or greater
- Can be used as a debonding layer between sub-base and base slabs.
- Breaks down after 30-35 days subject to UV Exposure.

APPLICATION INSTRUCTIONS

Apply BossCure 800 to the surface of freshly finished concrete once concrete has hardened sufficiently not to be marked by the application process. Apply BossCure 800 undiluted at a rate of 1 Litre per 5 square meters.

BossCure 800 is best applied by a pump or airless sprayer with a minimum pressure of 40PSI, however it can also be applied using a brush, roller or broom.

BossCure 800 performs best when one complete coat is applied, until a continuous uniform film is achieved.

Continued over page...

CLEAN UP

Wash all tools and equipment in clean water immediately after use.

TYPICAL PROPERTIES

Appearance:	White milky Liquid
Coverage:	5m ² per litre
Viscosity:	0.02 pascal seconds
Solids:	30% or greater
Solubility in Water:	Negligible
Flash Point:	100°C
Solvents:	5% aromatics
Shelf Life:	6 Months Maximum
Dry Time:	Tack Free: 1 - 3 Hours
	Hard Dry: 4 - 8 Hours
	Trafficable: 24 Hours
Application Temperature:	10°C - 35°C
Application by:	Spray, Brush Roller or Broom
Packaging:	20L, 205L or 1000L
UN Number:	Not Applicable
Hazchem Code:	Not Applicable
Packaging Group:	Not Applicable
Poison Schedule:	Not Scheduled
Dangerous Goods Class:	Not Applicable

HEALTH & SAFETY

Avoid Contact with skin. Protective gloves and clothing are recommended when mixing or using this product.

Please refer to the full MSDS (Material safety data sheet) for this product, which is available from Allcon on request.

DISCLAIMER

Boss products are manufactured to the highest quality, and if used in the correct applications and in accordance with all directions, will produce quality and consistent results. However, Allcon Group Pty Ltd accepts no responsibility for inappropriate usage or faulty workmanship by the end user.

Product: BossCure 800

Issue Date: October 2020



TECHNICAL DATA SHEET

- Coatings
- Curing
- Waterproofing
- Moisture Proofing
- Protection
- Repair Products
- Primers
- Repellent

P: 1300 255 266
E: sales@allcongroup.com.au

www.allcongroup.com.au